QC ABSTRACT

NAME OF WORK: Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Steel	Bend test	One Test		1	1
		Tensile Test	One Test		1	1
		Yield Test	One Test		1	1
		ReBend test	One Test		1	1
6	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	RCC(M20)	Compressive Strength(7days and 28days)	5 sets /31-100 cum	92.92	10	10

DR-14

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore-97

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2023-05-02-02** **Date: 20-07-23**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-07-23
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 269:2015 Ordinary Portland cement Specification , IS 4031 (Part 4,5):1988 IS 4031 Part 1 (RA 2021) DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, (RA 2018) Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, (RA 2019) Determination of Soundness, Clause 5, Clause 6 IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, (RA 2019) Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11, (RA 2019)DETERMINATION OF DENSITY , Clause 6
Date of test	:	18-07-23
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 269:2015
1	Fineness by dry sieving (%)	2.15	–
2	Finess by Air permeablity method (m^2/kg,Min)	282.2	225m^2/kg, Min
3	Density (gm/cc)	3.15	–
4	Standard Consistency (%)	29.0%	Not specified
5	Initial Setting time	185 minutes	Not less than 30 minutes
6	Final Setting time	270 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Agency/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AR-14

Page 1/1

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2023-05-02-02
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. **Date: 16-08-23**
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-07-23
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 269:2015 Ordinary Portland cement Specification , IS 4031 (Part 4,5):1988 IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, (RA 2019) Determination of Compressive Strength, Clause 6
Date of test	:	18-07-23
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 269:2015
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	54.5N/mm^2	Not less than 53 N/mm^2

* The results obtained are satisfactory as per standard requirements:

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2023-05-02-02** **Date: 20-07-23**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	17-07-23
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2021 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	17-07-23

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : **15000** grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	374	374	2.5	97.5	90-100
3	20 mm	6738	7112	47.4	52.6	30-70
4	10 mm	5274	12386	82.6	17.4	10-35
5	4.75 mm	2081	14467	96.4	3.6	0-5
6	Pan	533	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2023-05-02-02** **Date: 20-07-23**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.5	
3	Specific Gravity	2.65	_
4	Bulk Density(Loose) (Kg/l)	1.49	_
5	Bulk Density(Compacted) (Kg/l)	1.51	_
6	Water Absorption(%)	0.25	_

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	CP-2023-05-02-02 **Date: 19-07-23**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-07-23
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2021 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	17-07-23

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	159	159	3.2	96.8	90-100
3	10 mm	2541	2700	54.0	46.0	25-55
4	4.75 mm	2117	4817	96.3	3.7	0-10
5	Pan	183	5000	100	0	_

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P.

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2023-05-02-02** **Date: 19-07-23**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.6	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	14.8	
3	Specific Gravity	2.62	–
4	Bulk Density(Loose) (Kg/l)	1.50	–
5	Bulk Density(Compacted) (Kg/l)	1.55	–
6	Water Absorption(%)	0.28	–
7	Aggregate crushing Value(%)	26.6	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	24.3	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2023-05-02-02** **Date: 19-07-23**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-07-23

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2021
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 17-07-23

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	35	35	3.5	96.5	90-100	90-100	90-100	95-100
3	2.36 mm	172	207	20.7	79.3	60-95	75-100	85-100	95-100
4	1.18 mm	116	323	32.3	67.7	30-70	55-90	75-100	90-100
5	600 micron	201	524	52.4	47.6	15-34	35-59	60-79	80-100
6	300 micron	217	741	74.1	25.9	5-20	8-30	12-40	15-50
7	150 micron	183	924	92.4	7.6	0-10	0-10	0-10	0-15
8	Pan	76	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

23-AUG-14

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2023-05-02-02** **Date: 19-07-23**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.94	–
2	Specific Gravity	2.55	–
3	Material finer than 75 micron(%)	7.6	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2023-05-02-02**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore. **Date: 18-07-23**
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-07-23
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2019.
Date of test	:	17-07-23

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

End of Report*

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2023-05-02-02** **Date: 08-08-23**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-08-23
Sample Type /Size	:	Precast Cover Slab (100mm Thick)
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete
Date of test	:	04/08/2023
Grade of Slab	:	M15

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	77.51	100.48	1.116	4718	80.9	17.1	15.9	19.9
2	Cover Slab-2	77.49	100.52	1.122	4715	82.3	17.5	16.2	20.3
3	Cover Slab-3	77.50	100.51	1.118	4716	81.5	17.3	16.1	20.1

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL| ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02** **Date: 10/08/2023**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, IIIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-08-23

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.74 X 150.62 X 150.24	22705	8.220	321.1	14.1	14.2
2	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.29 X 150.01 X 150.73	22545	8.162	323.9	14.4	
3	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.33 X 150.44 X 150.84	22616	8.208	317.2	14.0	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02**

Date: 31/08/2023

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, IIIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-08-23

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.44 X 150.49 X 150.66	22641	8.433	533.8	23.6	23.2
2	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.52 X 150.10 X 150.09	22592	8.979	522.4	23.1	
3	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.90 X 150.45 X 150.67	22702	8.571	523.1	23.0	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/08/2023

Lab ID	:	CP-2023-05-02-02
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-08-23
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	10/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.53 X 150.36 X 150.82	22633	8.417	325.8	14.4	14.5
2	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.13 X 150.92 X 150.04	22658	8.857	332.1	14.7	
3	Drain Bottom Raft Concrete	M20	03/08/2023	10/08/2023	150.97 X 150.12 X 150.20	22665	8.514	326.7	14.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02** **Date: 31/08/2023**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-08-23

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.67 X 150.18 X 150.07	22628	8.501	540.9	23.9	23.7
2	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.64 X 150.78 X 150.63	22715	8.468	529.2	23.3	
3	Drain Bottom Raft Concrete	M20	03/08/2023	31/08/2023	150.10 X 150.39 X 150.99	22574	8.108	537.0	23.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE-14

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Date: 14/08/2023

Lab ID	:	CP-2023-05-02-02
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-23
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	14/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.07 X 150 72 X 150 18	22620	8.876	324.9	14.4	14.4
2	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.90 X 150.76 X 150.30	22750	8.858	325.2	14.3	
3	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.44 X 150.77 X 150.57	22682	8.675	331.2	14.6	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIKRECHAN
Authorized Signatory
Quality Manager

AB-14

Page 1/1
****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2023-05-02-02 **Date: 04/09/2023**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-08-23

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/09/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.02 X 150.42 X 150.19	22567	8.166	527.9	23.4	23.5
2	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.80 X 150.39 X 150.61	22678	8.553	524.3	23.1	
3	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.80 X 150.57 X 150.62	22705	8.163	544.0	24.0	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02** **Date: 14/08/2023**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-08-23

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.76 X 150.00 X 150.99	22615	8.923	321.1	14.2	14.4
2	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.40 X 150.96 X 150.21	22705	8.382	327.5	14.4	
3	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.34 X 150.66 X 150.76	22649	8.964	328.9	14.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Date: 04/09/2023

Lab ID	:	CP-2023-05-02-02
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)
Agency	:	Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.
Customer's Reference	:	BBMP/EE/BTP/WO/138/2022-23
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-23
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5
Date of test	:	04/09/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.89 X 150.08 X 150.28	22646	8.772	530.2	23.4	23.3
2	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.06 X 150.38 X 150.84	22565	8.940	520.5	23.1	
3	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.90 X 150.73 X 150.01	22746	8.772	535.4	23.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02**

Date: 14/08/2023

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-08-23

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 14/08/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.40 X 150.76 X 150.46	22674	8.261	323.6	14.3	14.5
2	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.11 X 150.51 X 150.63	22592	8.349	333.1	14.7	
3	Drain Side Wall Concrete	M20	07/08/2023	14/08/2023	150.54 X 150.64 X 150.25	22676	8.161	327.8	14.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2023-05-02-02** **Date: 04/09/2023**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Venkatagiriyappa layout, Seethappa layout Roads and Surrounding Areas in Ward No.14 (Vidyaranyapura)

Agency : Sri. D A Ravindra, No.1265, HIG, Mother Dairy Road, Near Karnataka Bank, Yelahanka New Town, Bengaluru-64.

Customer's Reference : BBMP/EE/BTP/WO/138/2022-23

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 09-08-23

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/09/2023

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.74 X 150.56 X 150.57	22696	8.327	522.2	23.0	23.3
2	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.37 X 150.59 X 150.22	22644	8.886	525.5	23.2	
3	Drain Side Wall Concrete	M20	07/08/2023	04/09/2023	150.37 X 150.63 X 150.98	22651	8.105	538.7	23.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Agency/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
B.B.M.P, Bangalore - 97